

## HAAS DOOR PAINTING INSTRUCTIONS

*Any garage door surface to be repainted must be properly prepared to assure the continued performance of the coating system. The following instructions must be followed to ensure proper repainting results.*

1. Dirt, loose chalk and mildew must be removed prior to repainting. Heavier dirt accumulations must be addressed prior to repainting by the use of a dilute solution of Spic and Span (1 cup to 5 gallons of warm water). Always rinse the surface thoroughly to remove any of the cleaning agents.
2. Minor scratches, which have not left the metal substrate exposed, can be lightly sanded or buffed to create a smoother surface. Care must be taken, however, not to expose the substrate. Once this exposed metal condition exists, the likelihood of rusting is greatly increased. Should the metal substrate be observed during this operation, see the following paragraph **\*\*DO NOT USE STEEL WOOL\*\***
3. Exposed metal must be treated to prevent rust from forming. To do so, sand the general area lightly and use a primer specifically designed to protect any exposed galvanized steel metal from corrosion. Allow sufficient time for the primer to dry before applying the topcoat. If either red or whit rust is evident, scrape or brush away as much rust as possible and then sand lightly, removing ALL rust before priming, care must be taken, however, not to destroy the galvanized surface.
4. After the door has been properly prepared, it must be coated within 24 hours using high quality latex exterior house paint. The surface must be completely dry prior to painting. Painting should not be done in the early morning. Avoid painting at temperatures below 50F. Follow the paint manufacturer's recommendations to apply a uniform coat at the proper thickness.

*CAUTION: Use of paints containing linseed oil, lacquer or alkyd base solvents voids the warranty of this door.*